

Conical Mandrel Tester

Determine flexibility of painted panels which are clamped and formed round the conical mandrel by rotation of the roller frame. The mandrel is tapered from 1 ½" to 1/8" along its length.

Mandrel marking from 37 mm to 6 mm diameter. After test the panels are examined to determine minimum diameter at which failure by elongation occurs.

Range 38 mm to 3mm dia.

Complies with ASTM D 522, BS 3900 - E11, ISO 686

Ref.: 116

